

VEarth VG 3150 W geotextile fabric is manufactured using high tenacity polypropylene yarns that are woven to form a dimensionally stable network, which allows the yarns to maintain their relative position.

VEarth VG 3150 W geotextile fabric resists ultraviolet deterioration, rotting, and biological degradation and is inert to commonly encountered soil chemicals



FILTRATION



STABILIZATION

TECHNICAL DATA SHEET

PROPERTY	TEST METHOD	TYPICAL ENGLISH	TYPICAL METRIC
Tensile Strength (Grab)	ASTM D4632	150 x 150 lbs	667.5 x 667.5 N
Elongation (Grab)	ASTM D4632	15% x 15%	15% x 15%
Trapezoidal Tear Strength	ASTM D4533	65 x 65 lbs	289.3 x 289.3 N
CBR Puncture	ASTM D6241	450 lbs	2,002.5 N
UV Resistance (500 hrs)	ASTM D4355	70%	70%
Apparent Opening Size*	ASTM D4751	40 US Std. Sieve	0.425 mm
Permittivity	ASTM D4491	0.05 sec ⁻¹	0.05 sec ⁻¹
Water Flow Rate	ASTM D4491	4 gpm/ft ²	163 lpm/m ²

*Maximum Average Roll Value

PROPERTY	TEST METHOD	TYPICAL ENGLISH	TYPICAL METRIC
Roll Dimensions	Measured	12.5 ft x 360 ft	3.81 x 109.8 m
		15 ft x 300 ft	4.6 x 91.5 m
		17.5 x 258 ft	5.3 x 78.7 m
Roll Area	Measured	500 yd ²	418 m ²